Last Patch™ Limestone

Patching Compound

Last Patch Limestone is a uniquely designed patching compound for limestone and sandstone. Used for aesthetic patches and repairs on coarse grained stones, concrete and masonry substrates. Because of its special properties, Last Patch camouflages its patchwork by absorbing water just like the porous stone surrounding it.

Product Information

- Absorbs water similar to stone
- UV stable, no color change
- Can be used below freezing temperatures
- Can be color matched
- Mix Ratio: 7:1 by weight or volume
- Set up time: 45 mintes @ 75F
- For faster set-times use **Universal Accelerator**
- For color matching use **Powdered Tints**

Applications

- Structural patch
- Repairing broken corners on limestone or sandstone
- Repairing chips and spalls in stone
- Crack repair in limestone panels
- Repairing sign holes in exterior buildings
- Patching exterior pavers
- Ideal for limestone step and sill repairs

Availalbe in Quart Kits

- 1 Qt A / 4 Tubes B)

Colors Available

- Indiana Buff
- Indiana Gray
- Texas Cream
- Cottonwood
- Silverdale
- Blue Stone
- Indiana Silver Buff
- Leuders buff
- Beaumaniere Brown

Unsanded Sanded

Before



Patch Before Grinding



After Grinding

BONSTONE® • MATERIALS CORPORATION • ~ Since 1962 ~

800-425-2214
info@bonstone.com
WWW.BONSTONE.COM

BONSTONE®
• MATERIALS CORPORATION •
est. 1962

707 Swan Drive
Mukwonago, WI 53149
800-425-2214
tel 262-363-9877 fax 262-363-9879
www.bonstone.com info@bonstone.com

TECHNICAL DATA SHEET

FILE UNDER DIV. 4

Last Patch™ Limestone

Product Description

A kit packaged exterior grade stone repair compound. Overfill of patch area and grinding flush. The patch area resembles limestone texture. This product exhibits far superior color stability and strength in freeze thaw conditions.

Mixed Properties	***Values***	
Mix ratio (7:1 by weight or volume)	Part A is in a metal container 1 tube part B quart kit packaged (use entire kit or mix small amount with enclosed measuring cups) part A in quart container, 4 tubes part B	
Mixed viscosity at 75°F	General mortar consistency	
Pot life at 75°F	2 minutes - Standard high speed version	
Set time at 75°F	45 minutes	
Set time at 75°F w/Accelerator	15 minutes	
Dry grind	2 hours	
90% cure	1 - 2 hours	
		Test Methods
Strengths		
Cohesive		
Tensile	354.6 psi	ASTM D-638
Compressive	1,437 psi	ASTM D-695
Adhesive *(on limestone)*		
Tensile		ASTM C-321
Shear	522.6 psi	ASTM D-905
Moduli		
Cohesive		
Tensile	16,436 psi	ASTM D-638
Compressive	12,810 psi	ASTM D-695
Elongation		
Cohesive		
Tensile *(at break)*	2.425%	ASTM D-638

This information is furnished without warranty, representation, inducement, or license of any kind, except that it is accurate to the best of Bonstone Materials Corporation's (BMC) knowledge or obtained from sources believed by BMC to be accurate, and BMC does not assume any legal responsibility for use or reliance upon same. User must determine if the product, process, or information described herein is suitable to the intended application. Before using any chemical, read its label and Material Safety Data Sheet.